### Consent Order of Dismissal, Section III.7 Z-Area Saltstone Disposal Facility Permit General Condition B.5.a-h Information

Permit	Requirement	Value	Comments
<b>Condition B.5</b> a)	Cumulative process volume of	1,805 kilogallons (kgals)	
,	salt waste disposed to date		
b)		631 kgals,	
	grout disposed and vault	Vault 4, Cells D, K	
	location (cell identity) for the		
c)	reporting period Cumulative process volume of	3,257 kgals	
	saltstone grout disposed to date	3,237 Kguis	
d)	Remaining vault volume	$9.37 \times 10^3 \text{ kgals}$	
e)	Curies disposed and vault	61 kilocuries (kCi),	
	location for the reporting	Vault 4, Cell D, K	
	period		
f)	5	195 kCi,	
	curies disposed to date	Vault 4, Cells D, E, F, L, K	
g)	Curies of highly radioactive	61 kCi,	
	radionuclides disposed and	Vault 4, Cell D, K	
	vault location for the reporting		
	period		
h)	Cumulative inventory of	194 kCi,	
	highly radioactive	Vault 4, Cells D, E, F, L, K	
	radionuclides disposed to date		

### Consent Order of Dismissal, Section III.7 (1) Chemical and Radiological Composition of Salt Waste

Chemical Name	Concentration (mg/L)
Major Constituent	
Water [H <sub>2</sub> 0]	8.12E+05
Solvated Ions	
Aluminate [Al(OH) <sub>4</sub> ]	1.59E+04
Carbonate $[C0_3^2]$	8.71E+03
Chloride [Cl]	4.84E+02
Fluoride [F]	2.40E+02
Hydroxide [OH]	1.52E+04
Nitrate [NO <sub>3</sub> ]	1.33E+05
Nitrite [NO <sub>2</sub> ]	8.29E+03
Sulfate [SO <sub>4</sub> <sup>2</sup> ]	5.47E+03
RCRA Hazardous Metals	
Arsenic [As]	2.05E-01
Barium [Ba]	9.59E-01
Cadmium [Cd]	2.68E-01
Chromium [Cr]	3.98E+01
Lead [Pb]	1.00E+00
Mercury [Hg]	1.41E+01
Selenium [Se]	3.12E-01
Silver [Ag]	8.53E-01
Other Metals	
Aluminum [Al]	4.53E+03
Boron [B]	5.95E+00
Cobalt [Co]	7.43E-02
Copper [Cu]	9.67E-01
Iron [Fe]	1.24E+02
Lithium [Li]	<2.36E-01
Manganese [Mg]	6.22E+01
Molybdenum [Mo]	4.83E+00
Nickel [Ni]	1.03E+01
Sodium [Na]	8.51E+04
Strontium [Sr]	7.21E-01
Zinc [Zn]	9.97E+00
Organic Compounds	
Tetraphenyl borate $[B(C_6H_5)^4]$	9.85E+00
Total Organic Carbon	7.42E+02
Total Insoluble Solids	
Total Insoluble Solids	4.55E+03

### Consent Order of Dismissal, Section III.7 (1) Chemical and Radiological Composition of Salt Waste (continued)

Radionuclide	Concentration (pCi/mL)
H-3	1.60E+03
C-14	5.27E+02
Co-60	6.65E+00
Ni-59	<1.36E+02
Ni-63	1.19E+02
Se-79	5.32E+02
Sr-90	2.64E+05
Y-90	2.64E+05
Tc-99	3.41E+04
Ru-106	<9.19E+01
Rh-106	<9.19E+01
Sb-125	7.12E+03
Te-125m	7.12E+03
I-129	9.01E+00
Cs-134	<7.21E+02
Cs-137	2.25E+07
Ba-137m	2.13E+07
Ce-144	<1.20E+02
Pr-144	<1.20E+02
Pm-147	<3.317E+03
Eu-154	2.82E+02
Np-237 (a) (t <sub>1/2</sub> )>5yr	<1.63E+01
Pu-238 (a) $(t_{1/2}) > 5$ yr	3.41E+04
Pu-239 (a) $(t_{1/2}) > 5 \text{ yr}$	1.07E+03
Pu-240 (a) $(t_{1/2}) > 5 \text{ yr}$	1.07E+03
Pu-241	2.72E+04
Pu-242 (a) $(t_{1/2}) > 5 \text{ yr}$	<8.82E+01
Am-241 (a) $(t_{1/2}) > 5$ yr	7.75E+02
Am-242m	8.29E+01
Cm-242 (a)	6.89E+01
Cm-244 (a) (t <sub>1/2</sub> )>5yr	2.23E+03
Cm-245 (a) $(t_{1/2}) > 5$ yr	<1.86E+01
Total Transuranic Alpha	
Emitters with $(t_{1/2}) > 5$ years	<4.43E+04

### Consent Order of Dismissal, Section III.7 (1) Chemical and Radiological Composition of Salt Waste

The grout formulation is defined by the proportions of dry premix components (Type II Portland cement, Class F flyash, and Grade 120/100 slag) and the ratio of the water content in the salt waste to dry premix. Small quantities of admixtures are added as required for the purposes of set retardant and anti-foam. These have an insignificant effect on the overall grout composition (less than 0.2 wt% of the overall grout composition).

The formulation used for the reporting period is shown below:

#### **Saltstone Dry Premix Composition**

Component	Weight %	
Type II Portland cement	10	
Class F flyash	45	
Grade 120/100 slag	45	

Water to Premix Ratio (by weight) — 0.60

Utilizing this grout formulation leads to an overall grout composition as shown below:

#### **Overall Grout Composition**

Component	Weight %
Salt Waste	41
Type II Portland cement	6
Grade 120/100 slag	27
Class F flyash	27

## Consent Order of Dismissal, Section III.7 (3) Chemical and Radiological Composition of Saltstone (continued)

Chemical Name	Concentration (mg/L)
Major Constituent	
Water [H <sub>2</sub> O]	5.3E+05
Portland (II) Cement	1.0E+05
Class F Flyash	4.7E+05
Grade 100/120 Slag	4.7E+05
Solvated Ions	1.72.00
Aluminate [Al(OH) <sub>4</sub> ]	1.0E+04
Carbonate $[C0_3^2]$	5.7E+03
Chloride [Cl]	3.1E+02
Fluoride [F]	1.6E+02
Hydroxide [OH]	9.9E+03
Nitrate [NO <sub>3</sub> ]	8.7E+04
Nitrite [NO <sub>2</sub> ]	5.4E+03
Sulfate $[SO_4^2]$	3.6E+03
RCRA Hazardous Metals	
Arsenic [As]	1.3E-01
Barium [Ba]	6.2E-01
Cadmium [Cd]	1.7E-01
Chromium [Cr]	2.6E+01
Lead [Pb]	6.5E-01
Mercury [Hg]	9.2E+00
Selenium [Se]	2.0E-01
Silver [Ag]	5.6E-01
Other Metals	
Aluminum [Al]	2.9E+03
Boron [B]	3.9E+00
Cobalt [Co]	4.8E-02
Copper [Cu]	6.3E-01
Iron [Fe]	8.1E+01
Lithium [Li]	1.5E-01
Manganese [Mg]	4.0E+01
Molybdenum [Mo]	3.1E+00
Nickel [Ni]	6.7E+00
Sodium [Na]	5.5E+04
Strontium [Sr]	4.7E-01
Zinc [Zn]	6.5E+00
Organic Compounds	
Tetraphenyl borate $[B(C_6H_5)^4]$	6.4E+00
Total Organic Carbon	4.8E+02
Total Insoluble Solids	
Total Insoluble Solids	3.0E+03

### Consent Order of Dismissal, Section III.7 (3) Chemical and Radiological Composition of Saltstone (continued)

Radionuclide	Concentration (pCi/mL)
H-3	1.0E+03
C-14	3.4E+02
Co-60	4.3E+00
Ni-59	8.9E+01
Ni-63	7.8E+01
Se-79	3.5E+02
Sr-90	1.7E+05
Y-90	1.7E+05
Tc-99	2.2E+04
Ru-106	6.0E+01
Rh-106	6.0E+01
Sb-125	4.6E+03
Te-125m	4.6E+03
I-129	5.9E+00
Cs-134	4.7E+02
Cs-137	1.5E+07
Ba-137m	1.4E+07
Ce-144	7.8E+01
Pr-144	7.8E+01
Pm-147	2.2E+03
Eu-154	1.8E+02
Np-237 (a) (t <sub>1/2</sub> ) > 5 yr	1.1E+01
Pu-238 (a) (t <sub>1/2</sub> ) >5 yr	2.2E+04
Pu-239 (a) (t <sub>1/2</sub> ) >s yr	7.0E+02
Pu-240 (a) (t <sub>1/2</sub> ) >s yr	7.0E+02
Pu-241	1.8E+04
Pu-242 (a) (t <sub>1/2</sub> ) >5 yr	5.7E+01
Am-241 (a) (t <sub>1/2</sub> )> 5 yr	5.0E+02
Am-242m	5.4E-01
Cm-242 (a)	4.5E-01
Cm-244 (a) (t <sub>1/2</sub> ) > 5 yr	1.5E+03
Cm-245 (a) (t <sub>1/2</sub> ) > <b>5</b> yr	1.2E+01
Total Transuranic Alpha	<2.9E+04
Emitters with $(t_{1/2})$ > 5 years	