Z-Area Saltstone Disposal Facility Permit General Condition B.5.a-h Information and Consent Order of Dismissal, Section III.7

Permit Condition	Requirement	Estimated Value	Updated Value	Comments
B.5 a)	Cumulative process volume of salt waste disposed to date	Not Applicable	13,485.15 kgal SDU 4, Cells B, D, E, F, H, J, K, L SDU 2, Cells A and B SDU 5, Cells A and B SDU 3, Cell A SDU 6	
b)	Process volume of saltstone grout disposed and vault/disposal unit location (including cell identity) for the reporting period	Not Applicable	0.00 kgal SDU 6	
c)	Cumulative process volume of saltstone grout disposed-to- date	Not Applicable	23,118.1 kgal SDU 4, Cells B, D, E, F, H, J, K, L SDU 2, Cells A and B SDU 5, Cells A and B SDU 3, Cell A SDU 6	
d)	Remaining vault/disposal unit volume	Not Applicable	4,917.6 kgal SDU 3, Cells A and B 31,529.9 kgal SDU 6	The remaining vault/disposal unit volume shown for SDU 3 is based on a fill height of 21.5 feet and SDU 6 is based on 41 feet. Currently, due to Saltstone Safety Basis assumptions, the fill height of SDUs 3 and 6 are restricted to less than these heights.
e)	Curies disposed and vault/disposal unit location for the reporting period	0.00 kCi SDU 6		
f)	Cumulative inventory of curies disposed-to-date	475.9 kCi SDU 4, Cells B, D, E, F, H, J, K, L SDU 2, Cells A and B SDU 5, Cells A and B SDU 3, Cell A SDU 6		
g)	Curies of highly radioactive radionuclides disposed and vault/disposal unit location for the reporting period	0.00 kCi SDU 6		
h)	Cumulative inventory of highly radioactive radionuclides disposed-to-date	475.6 kCi SDU 4, Cells B, D, E, F, H, J, K, L SDU 2, Cells A and B SDU 5, Cells A and B SDU 3, Cell A SDU 6		

Consent Order of Dismissal, Section III.7 (1) Chemical and Radiological Composition of Salt Waste

Chemical Name	Estimated Concentration (mg/L)	Updated Concentration (mg/L)
Major Constituent		
Water [H ₂ O]	9.206E+05	
Solvated Ions		
Aluminate [Al(OH) ₄]	1.38E+04	
Carbonate [CO ₃ ²⁻]	2.09E+04	
Chloride [Cl ⁻]	4.74E+02	
Fluoride [F ⁻]	1.00E+02	
Hydroxide [OH ⁻]	3.13E+04	
Nitrate [NO ₃ ⁻]	9.06E+04	
Nitrite [NO ₂ ⁻]	2.14E+04	
Sulfate [SO ₄ ²⁻]	6.85E+03	
RCRA Hazardous Metals		
Arsenic [As]	3.02E-01	
Barium [Ba]	9.15E+00	
Cadmium [Cd]	2.10E-01	
Chromium [Cr]	3.87E+01	
Lead [Pb]	3.38E-01	
Mercury [Hg]	6.76E+01	
Selenium [Se]	3.02E-01	
Silver [Ag]	6.41E-01	
Other Metals		
Aluminum [Al]	3.93E+03	
Boron [B]	3.27E+01	
Cobalt [Co]	2.01E-02	
Copper [Cu]	1.46E+00	
Iron [Fe]	9.41E+00	
Lithium [Li]	4.55E+00	
Manganese [Mn]	1.28E+00	
Molybdenum [Mo]	1.40E+01	
Nickel [Ni]	1.02E+00	
Sodium [Na]	4.94 M	
Strontium [Sr]	4.15E-02	
Zinc [Zn]	7.63E+00	
Organic Compounds		
Tetraphenylborate $[B(C_6H_5)^{4-}]$		
]	5.00E+00	
Total Organic Carbon	2.04E+02	
Total Insoluble Solids	0.005.00	
Total Insoluble Solids	0.00E+00	

SRR-ESH-2019-00142 Revision 0 Post Date: December 27, 2019 Page 2 of 6

Consent Order of Dismissal, Section III.7 (1) Chemical and Radiological Composition of Salt Waste (continued)

Radionuclide	Estimated Concentration	Updated Concentration
	(pCi/mL)	(pCi/mL)
H-3	7.86E+02	
C-14	4.92E+02	
Ni-59	6.08E-01	
Co-60	3.64E-01	
Ni-63	3.04E+01	
Se-79	2.60E+01	
Sr-90	1.83E+05	
Y-90	1.83E+05	
Tc-99	3.22E+04	
Rh-106	5.50E+00	
Ru-106	5.50E+00	
Sb-125	3.00E+01	
Te-125m	3.00E+01	
I-129	2.23E+01	
Cs-134	6.57E-02	
Cs-137	1.95E+06	
Ba-137m	1.84E+06	
Ce-144	2.37E-04	
Pr-144	2.37E-04	
Pm-147	4.41E+01	
Eu-154	8.60E-01	
Np-237 (a) $(t_{1/2}) > 5 \text{ yr}$	1.42E+01	
Pu-238 (a) $(t_{1/2}) > 5 \text{ yr}$	1.59E+04	
Pu-239 (a) $(t_{1/2}) > 5 \text{ yr}$	4.06E+02	
Pu-240 (α) (t _{1/2}) > 5 yr	4.06E+02	
Pu-241	4.70E+03	
Pu-242 (α) (t _{1/2}) > 5 yr	7.67E+01	
Am-241 (α) (t _{1/2}) > 5 yr	1.82E+01	
Am-242m	2.27E-01	
Cm-242 (α)	1.87E-01	
Cm-244 (α) (t _{1/2}) > 5 yr	6.25E+01	
Cm-245 (α) (t _{1/2}) > 5 yr	1.82E+00	
Total Transuranic Alpha Emitters with $(t_{1/2}) > 5$ years	2.80E+04	

Consent Order of Dismissal, Section III.7 (2) Formulation of Grout Used to Treat and Solidify the Salt Waste

The grout formulation is defined by the proportions of dry premix components (cement, thermally beneficiated flyash, and slag) and the ratio of the water content in the salt waste to dry premix. Small quantities of admixtures are added as required for the purposes of set retardant and anti-foam. These have an insignificant effect on the overall grout composition (0.2 wt% of the overall grout composition).

The formulation used for the reporting period is shown below:

Saltstone Dry Premix Composition

Component	Weight %
Cement	10
Thermally Beneficiated Flyash	45
Slag	45

Water to Premix Ratio (by weight) -0.630

The water to premix ratio reflects the pounds of free water added to the process for each pound of dry premix fed to the saltstone mixer averaged for the quarter.

Utilizing this grout formulation leads to an overall grout composition as shown below:

Overall Grout Composition

Component	Weight %
Salt Waste	44.0
Cement	5.59
Slag	25.2
Thermally Beneficiated Flyash	25.2

Consent Order of Dismissal, Section III.7 (3) Chemical and Radiological Composition of Saltstone

Chemical Name	Estimated Concentration (mg/L)	Updated Concentration (mg/L)
Major Constituent		
Water [H ₂ O]	5.80E+05	
Cement	9.67E+04	
Thermally Beneficiated Flyash	4.35E+05	
Slag	4.35E+05	
Solvated Ions		
Aluminate [Al(OH) ₄]	8.70E+03	
Carbonate [CO ₃ ²⁻]	1.32E+04	
Chloride [Cl ⁻]	2.99E+02	
Fluoride [F ⁻]	6.30E+01	
Hydroxide [OH ⁻]	1.97E+04	
Nitrate [NO ₃ ⁻]	5.71E+04	
Nitrite [NO ₂ -]	1.35E+04	
Sulfate [SO ₄ ²⁻]	4.32E+03	
RCRA Hazardous Metals		
Arsenic [As]	1.90E-01	
Barium [Ba]	5.77E+00	
Cadmium [Cd]	1.32E-01	
Chromium [Cr]	2.44E+01	
Lead [Pb]	2.13E-01	
Mercury [Hg]	4.26E+01	
Selenium [Se]	1.90E-01	
Silver [Ag]	4.04E-01	
Other Metals		
Aluminum [Al]	2.48E+03	
Boron [B]	2.06E+01	
Cobalt [Co]	1.27E-02	
Copper [Cu]	9.20E-01	
Iron [Fe]	5.93E+00	
Lithium [Li]	2.87E+00	
Manganese [Mn]	8.07E-01	
Molybdenum [Mo]	8.83E+00	
Nickel [Ni]	6.43E-01	
Sodium [Na]	7.16E+04	
Strontium [Sr]	2.62E-02	
Zinc [Zn]	4.81E+00	
Organic Compounds		
Tetraphenylborate $[B(C_6H_5)^{4-}]$	3.15E+00	
Total Organic Carbon	1.29E+02	
Total Insoluble Solids		
Total Insoluble Solids	0.00E+00	

SRR-ESH-2019-00142 Revision 0 Post Date: December 27, 2019 Page 5 of 6

Consent Order of Dismissal, Section III.7 (3) Chemical and Radiological Composition of Saltstone (continued)

Radionuclide	Estimated Concentration	Updated Concentration
	<u>(pCi/mL)</u>	<u>(pCi/mL)</u>
H-3	4.96E+02	
C-14	3.10E+02	
Ni-59	3.83E-01	
Co-60	2.29E-01	
Ni-63	1.92E+01	
Se-79	1.64E+01	
Sr-90	1.15E+05	
Y-90	1.15E+05	
Tc-99	2.03E+04	
Rh-106	3.47E+00	
Ru-106	3.47E+00	
Sb-125	1.89E+01	
Te-125m	1.89E+01	
I-129	1.41E+01	
Cs-134	4.14E-02	
Cs-137	1.23E+06	
Ba-137m	1.16E+06	
Ce-144	1.49E-04	
Pr-144	1.49E-04	
Pm-147	2.78E+01	
Eu-154	5.42E-01	
Np-237 (a) $(t_{1/2}) > 5 \text{ yr}$	8.95E+00	
Pu-238 (a) $(t_{1/2}) > 5 \text{ yr}$	1.00E+04	
Pu-239 (α) ($t_{1/2}$) > 5 yr	2.56E+02	
Pu-240 (α) ($t_{1/2}$) > 5 yr	2.56E+02	
Pu-241	2.96E+03	
Pu-242 (α) (t _{1/2}) > 5 yr	4.84E+01	
Am-241 (α) (t _{1/2}) > 5 yr	1.15E+01	
Am-242m	1.43E-01	
Cm-242 (a)	1.18E-01	
Cm-244 (α) (t _{1/2}) > 5 yr	3.94E+01	
Cm-245 (α) (t _{1/2}) > 5 yr	1.15E+00	
Total Transuranic Alpha		
Emitters with $(t_{1/2}) > 5$ years	1.77E+04	